

FORM PTO-1390 (Modified)
(REV 11-2000)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

215550US0XPCT

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

09/926507

INTERNATIONAL APPLICATION NO.

PCT/EP00/02780

INTERNATIONAL FILING DATE

30 March 2000

PRIORITY DATE CLAIMED

12 May 1999

TITLE OF INVENTION

PROCESS FOR PRODUCING INHERENTLY MICROBICIDAL POLYMER SURFACES

APPLICANT(S) FOR DO/EO/US

OTTERSACH Peter Zum Beuel et al.

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (24) indicated below.
4. ☒ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☐ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☒ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☒ is attached hereto.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☐ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
10. ☐ An English language translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).
11. ☐ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☒ A copy of the International Search Report (PCT/ISA/210).

Items 13 to 20 below concern document(s) or information included:

13. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☐ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
20. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
21. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
22. ☐ Certificate of Mailing by Express Mail
23. ☒ Other items or information:

Request for Consideration of Documents Cited in International Search Report/Request for Priority
PCT/IB/308

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR 1.492 (a)(1) - (5))	INTERNATIONAL APPLICATION NO.	ATTORNEY'S DOCKET NUMBER
09/926507	PCT/EP00/02780	215550US0XPCT

24. The following fees are submitted:

BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :

- ☐ Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO \$1040.00
- ☒ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$890.00
- ☐ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$740.00
- ☐ International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$710.00
- ☐ International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00

ENTER APPROPRIATE BASIC FEE AMOUNT =**CALCULATIONS PTO USE ONLY**

\$890.00

Surcharge of \$130.00 for furnishing the oath or declaration later than ☐ 20 ☒ 30 months from the earliest claimed priority date (37 CFR 1.492 (e)).

\$130.00

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE
Total claims	- 20 =	0	x \$18.00
Independent claims	- 3 =	0	x \$84.00

\$0.00

\$0.00

Multiple Dependent Claims (check if applicable). ☐

\$0.00

TOTAL OF ABOVE CALCULATIONS =

\$1,020.00

☒ Applicant claims small entity status. See 37 CFR 1.27). The fees indicated above are reduced by 1/2.

\$0.00

SUBTOTAL =

\$1,020.00

Processing fee of \$130.00 for furnishing the English translation later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (f)).

\$0.00

TOTAL NATIONAL FEE =

\$1,020.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable). ☐

\$0.00

TOTAL FEES ENCLOSED =

\$1,020.00

Amount to be refunded	\$
charged	\$

- a. ☒ A check in the amount of \$1,020.00 to cover the above fees is enclosed.
- b. ☐ Please charge my Deposit Account No. _____ in the amount of _____ to cover the above fees. A duplicate copy of this sheet is enclosed.
- c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 15-0030 A duplicate copy of this sheet is enclosed.
- d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. **Credit card information should not be included on this form.** Provide credit card information and authorization on PTO-2038.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

Surinder Sachar
Registration No. 34,423

**22850**

SIGNATURE

Norman F. Oblon

NAME

24,618

REGISTRATION NUMBER

DATE

Nov. 13 2001

Rec'd PCT/PTO 07 FEB 2002

215550US-0XPCT

#4/a

IN THE UNITED STATES PATENT & TRADEMARK OFFICE

IN RE APPLICATION OF: :
PETER OTTERSBACH ET AL : ATTN: APPLICATION DIVISION
SERIAL NO: 09/926,507 :
FILED: NOVEMBER 13, 2001 :
FOR: PROCESS FOR PREPARING
INHERENTLY MICROBICIDAL
POLYMER SURFACES

PRELIMINARY AMENDMENT

ASSISTANT COMMISSIONER FOR PATENTS
WASHINGTON, D.C. 20231

SIR:

Prior to examination on the merits, please amend the above-identified application as follows.

IN THE CLAIMS

Please cancel Claims 7-10.

Please amend the claims as shown on the marked-up copy following this amendment to read as follows.

1. (Amended) A process for preparing an antimicrobial polymer, said process comprising

polymerizing one or more aliphatically unsaturated monomers, said one or more aliphatically unsaturated monomers at least singly functionalized by means of a secondary amino group.

2. (Amended) The process as claimed in claim 1, wherein the one or more aliphatically unsaturated monomers are functionalized by means of a secondary amino group of formula



where R^1 is a branched, unbranched or cyclic, saturated or unsaturated hydrocarbon radical having up to 50 carbon atoms which may have substitution by O atoms, N atoms or S atoms, and

R^2 is a branched, unbranched or cyclic, saturated or unsaturated hydrocarbon radical having up to 25 carbon atoms, which may have substitution by O atoms, N atoms or S atoms.

3. (Amended) The process as claimed in claim 1, wherein the polymerization is carried out on a substrate.

4. (Amended) The process as claimed in claim 1, wherein the polymerization is carried out as a graft polymerization of a substrate.

Please add the following new claims.

11. (New) An article of manufacture comprising an antimicrobial coating, said antimicrobial coating comprising an antimicrobial polymer prepared by the process as claimed in claim 1.

12. (New) A medical device comprising an antimicrobial coating, said antimicrobial coating comprising an antimicrobial polymer prepared by the process as claimed in claim 1.

13. (New) A hygiene article comprising an antimicrobial coating, said antimicrobial coating comprising an antimicrobial polymer prepared by the process as claimed in claim 1.

14. (New) A surface coating, protective paint or other coating comprising an antimicrobial polymer prepared by the process as claimed in claim 1.

REMARKS

Claims 1-6 and 11-14 are active in the present application. Claims 7-10 have been canceled. Claims 1-4 have been amended to remove multiple dependencies and for clarity. Support for the new claims is found in the original claims. No new matter is believed to have been added. An action on the merits and allowance of claims is solicited.

Respectfully submitted,

OBLON, SPIVAK, McCLELLAND,
MAIER & NEUSTADT, P.C.



Norman F. Oblon
Attorney of Record
Registration No. 24,618

Stefan U. Koschmieder, Ph.D.
Registration No. 50,238



22850

(703) 413-3000
Fax #: (703) 413-2220
NFO/SUKOS/js

I:\atty\SUKOS\215550US-PR.wpd

Marked-Up Copy

Serial No: 09/926,507

Amendment Filed on:

2-7-02

IN THE CLAIMS

--1. (Amended) A process for preparing an antimicrobial polymer, said process comprising [polymers which comprises]

polymerizing one or more aliphatically unsaturated monomers, said one or more aliphatically unsaturated monomers [which have been] at least singly functionalized by means of a secondary amino group.

2. (Amended) The process as claimed in claim 1, wherein the one or more aliphatically unsaturated monomers are functionalized by means of a secondary amino group [and having the general] of formula



where R^1 is a branched, unbranched or cyclic, saturated or unsaturated hydrocarbon radical having up to 50 carbon atoms which may have substitution by O atoms, N atoms or S atoms, and

R^2 is a branched, unbranched or cyclic, saturated or unsaturated hydrocarbon radical having up to 25 carbon atoms, which may have substitution by O atoms, N atoms or S atoms[, are used].

3. (Amended) The process as claimed in claim 1 [or 2], wherein the polymerization is carried out on a substrate

4. (Amended) The process as claimed in [one of claims 1 to 3] claim 1, wherein the polymerization is carried out as a graft polymerization of a substrate.

Claims 7-10 (Canceled).

Claims 11-14 (New).--

Docket No. 215550US0XPCT

IN RE APPLICATION OF: Peter OTTERSBACH et al.

SERIAL NO: 09/926,507

FILED: November 13, 2001

FOR: PROCESS FOR PREPARING INHERENTLY MICROBICIDAL POLYMER SURFACES

ASSISTANT COMMISSIONER FOR PATENTS
WASHINGTON, D.C. 20231

SIR:

Transmitted herewith is an amendment in the above-identified application.

☒ No additional fee is required

☐ Small entity status of this application under 37 C.F.R. §1.9 and §1.27 is claimed.

☒ Additional documents filed herewith: Notification of Missing Requirements/Response to Notification of Missing Requirements/Declaration/Amended Sheets (Pages 7, 15, and 16)
PCT Transmittal Letter/Information Disclosure Statement/Form PTO-1449

The Fee has been calculated as shown below:

CLAIMS	CLAIMS REMAINING		HIGHEST NUMBER PREVIOUSLY PAID	NO. EXTRA CLAIMS	RATE	CALCULATIONS	
TOTAL	10	MINUS	20	0	× \$18 =	\$0.00	
INDEPENDENT	1	MINUS	3	0	× \$84 =	\$0.00	
		<input type="checkbox"/> MULTIPLE DEPENDENT CLAIMS			+ \$280 =	\$0.00	
		TOTAL OF ABOVE CALCULATIONS					\$0.00
		<input type="checkbox"/> Reduction by 50% for filing by Small Entity					\$0.00
		<input type="checkbox"/> Recordation of Assignment			+ \$40 =	\$0.00	
		TOTAL					\$0.00

☐ A check in the amount of _____ is attached.

- ☒ Please charge any additional Fees for the papers being filed herewith and for which no check is enclosed herewith, or credit any overpayment to deposit Account No. 15-0030. A duplicate copy of this sheet is enclosed.
- ☒ If these papers are not considered timely filed by the Patent and Trademark Office, then a petition is hereby made under 37 C.F.R. §1.136, and any additional fees required under 37 C.F.R. §1.136 for any necessary extension of time may be charged to Deposit Account No. 15-0030. A duplicate copy of this sheet is enclosed.

OBLON, SPIVAK, McCLELLAND,
MAIER & NEUSTADT, P.C.

Norman F. Oblon

Norman F. Oblon
Registration No. 24,618

Surinder Sachar
Registration No. 34,423



22850

Customer Number 22850
Tel. (703) 413-3000
Fax. (703) 413-2220
(OSMMN 10/01)

Docket No. 215550US0XPCT

IN RE APPLICATION OF: Peter OTTERSBAACH et al.

SERIAL NO: 09/926,507

FILED: November 13, 2001

FOR: PROCESS FOR PREPARING INHERENTLY MICROBICIDAL POLYMER SURFACES

ASSISTANT COMMISSIONER FOR PATENTS
WASHINGTON, D.C. 20231

SIR:

Transmitted herewith is an amendment in the above-identified application.

- ☒ No additional fee is required
- ☐ Small entity status of this application under 37 C.F.R. §1.9 and §1.27 is claimed.
- ☒ Additional documents filed herewith: Notification of Missing Requirements/Response to Notification of Missing Requirements/Declaration/Amended Sheets (Pages 7, 15, and 16)
PCT Transmittal Letter/Information Disclosure Statement/Form PTO-1449

The Fee has been calculated as shown below:

CLAIMS	CLAIMS REMAINING		HIGHEST NUMBER PREVIOUSLY PAID	NO. EXTRA CLAIMS	RATE	CALCULATIONS
TOTAL	10	MINUS	20	0	× \$18 =	\$0.00
INDEPENDENT	1	MINUS	3	0	× \$84 =	\$0.00
		<input type="checkbox"/> MULTIPLE DEPENDENT CLAIMS			+ \$280 =	\$0.00
		TOTAL OF ABOVE CALCULATIONS				\$0.00
		<input type="checkbox"/> Reduction by 50% for filing by Small Entity				\$0.00
		<input type="checkbox"/> Recordation of Assignment			+ \$40 =	\$0.00
		TOTAL				\$0.00

☐ A check in the amount of _____ is attached.

- ☒ Please charge any additional Fees for the papers being filed herewith and for which no check is enclosed herewith, or credit any overpayment to deposit Account No. 15-0030. A duplicate copy of this sheet is enclosed.
- ☒ If these papers are not considered timely filed by the Patent and Trademark Office, then a petition is hereby made under 37 C.F.R. §1.136, and any additional fees required under 37 C.F.R. §1.136 for any necessary extension of time may be charged to Deposit Account No. 15-0030. A duplicate copy of this sheet is enclosed.

OBLON, SPIVAK, McCLELLAND,
MAIER & NEUSTADT, P.C.

Norman F. Oblon

Norman F. Oblon

Registration No. 24,618

Surinder Sachar

Registration No. 34,423



22850

Customer Number 22850
Tel. (703) 413-3000
Fax. (703) 413-2220
(OSMMN 10/01)

Process for preparing inherently microbicidal polymer surfaces

The invention relates to a process for preparing antimicrobial polymers by polymerization of amino-functionalized monomers and to the use of antimicrobial polymers prepared in this way.

The invention also relates to a process for preparing antimicrobial polymers by graft-polymerizing amino-functionalized monomers on a substrate and to the use of antimicrobial substrates prepared in this way.

It is highly undesirable for bacteria to become established or to spread on the surfaces of pipelines, containers or packaging. Frequently, slime layers form and permit sharp rises in microbial populations, and these can lead to persistent impairment of the quality of water, drinks or foods, and even to spoilage of the product and harm to the health of consumers.

Bacteria must be kept away from all fields of life in which hygiene is important. This affects textiles for direct body contact, especially in the genital area, and for the care of the elderly and sick. Bacteria must also be kept away from surfaces of furniture and instruments in wards, especially in areas for intensive care and neonatal care, in hospitals, especially in areas for medical interventions, and in isolation wards for critical cases of infection, and also in toilets.

A current method of treating equipment, or the surfaces of furniture or textiles, to resist bacteria either when this becomes necessary or else as a precautionary measure, is to use chemicals or solutions of mixtures of these which, as disinfectants, have a fairly broad general antimicrobial action. Chemical agents of this type act nonspecifically and are frequently themselves toxic or irritant, or form degradation products which are hazardous to health. In addition, people frequently exhibit intolerance to these materials once they have become sensitized.

Another method to counteract surface spread of bacteria is to incorporate substances with antimicrobial action into a matrix.

5 Tert-butylaminoethyl methacrylate is a commercially available monomer in methacrylate chemistry and is used in particular as a hydrophilic constituent in copolymerizations. For example, EP-B 0 290 676 uses various polyacrylates and polymethacrylates as a matrix for immobilizing bactericidal quaternary ammonium compounds.

10 In another technical sector US-A 4 532 269 discloses a terpolymer of butyl methacrylate, tributyltin methacrylate and tert-butylaminoethyl methacrylate. This polymer is used as an antimicrobial paint for ships: the hydrophilic tert-butylaminoethyl methacrylate promotes gradual erosion of the polymer, thus liberating the highly toxic tributyltin methacrylate as antimicrobial agent.

15 In these applications the copolymer prepared using aminomethacrylates is merely a matrix or carrier substance for added microbicidal agents which can diffuse or migrate out of the carrier substance. Sooner or later polymers of this type lose their effectiveness once the "minimal inhibitory concentration"
20 (MIC) is no longer achieved on the surface.

European Patent Applications 0 862 858 and 0 862 859 have disclosed that homo- and copolymers of tert-butylaminoethyl methacrylate with a methacrylate having a secondary amino function have inherent microbicidal
25 properties. To avoid undesirable resistance phenomena in the microbes, particularly bearing in mind the development of resistance by bacteria known from antibiotics research, systems developed in the future will need to continue to be based on novel compositions and have improved effectiveness.

30 The object of the present invention is therefore to develop novel polymers having antimicrobial action. These, where appropriate in the form of a coating, should prevent the establishment and spread of bacteria on surfaces.

Surprisingly, it has now been found that polymerizing aliphatically unsaturated monomers which have been at least singly functionalized by means of a secondary amino group gives polymers with a long-lasting microbicidal surface which is not attacked by solvents or by physical stresses and which does not exhibit migration. This makes it unnecessary to use other biocides.

The present invention provides a process for preparing antimicrobial polymers, which comprises polymerizing aliphatically unsaturated monomers which have been at least singly functionalized by means of a secondary amino group.

The aliphatically unsaturated monomers used in the process according to the invention and at least singly functionalized by means of a secondary amino group may have a hydrocarbon radical of up to 50 carbon atoms, preferably up to 30 carbon atoms, particularly preferably up to 22 carbon atoms. The substituents of the amino group may be aliphatic or vinylic hydrocarbon radicals, such as methyl, ethyl, propyl or acrylic radicals, or cyclic hydrocarbon radicals, such as substituted or unsubstituted phenyl or cyclohexyl radicals having up to 25 carbon atoms. The amino group may also have substitution by keto or aldehyde groups, such as acryloyl or oxo groups.

To achieve a sufficient rate of polymerization, the monomers used according to the invention should have a molar mass of less than 900, preferably less than 550 g/mol.

A particular embodiment of the present invention uses aliphatic unsaturated monomers functionalized by means of a secondary amino group and having the general formula



where R^1 is a branched, unbranched or cyclic, saturated or unsaturated hydrocarbon radical having up to 50 carbon atoms which

may have substitution by O atoms, N atoms or S atoms, and

R^2 is a branched, unbranched or cyclic, saturated or unsaturated hydrocarbon radical having up to 25 carbon atoms, which may have substitution by O atoms, N atoms or S atoms.

Suitable monomer building blocks, besides the secondary-amino-functionalized acrylates and methacrylates described in European Applications 0 862 858 and 0 862 859, are any aliphatically unsaturated monomers which have at least one secondary amino function, for example ethyl 3-phenylmethylamino-2-butenate, ethyl 3-ethylamino-2-butenate, ethyl 3-methylamino-2-butenate, 3-methylamino-1-phenyl-2-propen-1-one, N-4-methylamino-1-anthraquinoyl(2-methyl)acrylamide, N-9,10-dihydro-4-(4-methylphenylamino)-9,10-dioxo-1-anthraquinyl-2-methylpropenamide, propyl 2-hydroxy-3-(3-triethoxysilylpropylamino)-2-propenoate, 1-(1-methylethylamino)-3-(2-(2-propenyl)phenoxy)-2-propanol hydrochloride, ethyl 3-phenylamino-3-methyl-2-butenate, 1-(1-methylethylamino)-3-(2-(2-propenyloxy)phenoxy)-2-propanol hydrochloride, methyl 2-acrylamido-2-methoxyacetate, methyl 2-acetamidoacrylate, N-tert-butylacrylamide, 2-hydroxy-N-2-propenylbenzamide and N-methyl-2-propenamide.

The novel process can also be carried out by polymerizing the monomers at least singly functionalized by means of a secondary amino group on a substrate. This gives a physisorbed coating made from the antimicrobial copolymer on the substrate.

Suitable substrate materials are especially any of the polymeric plastics, such as polyurethanes, polyamides, polyesters and polyethers, polyether block amides, polystyrene, polyvinyl chloride, polycarbonates, polyorganosiloxanes, polyolefins, polysulfones, polyisoprene, polychloroprene, polytetrafluoroethylene (PTFE) or corresponding copolymers or blends, or also naturally occurring or synthetic rubbers, with or without radiation-sensitive groups. The novel process may also be used on surfaces of objects

09926507 020702

made from metal, from glass or from wood and surface-coated or otherwise coated with plastic.

In another embodiment of the present invention the antimicrobial polymers
5 may be obtained by graft-polymerizing a substrate with an aliphatically unsaturated monomer at least singly functionalized by means of a secondary amino group. The grafting of the substrate allows covalent linking of the antimicrobial polymer to the substrate. Substrates which may be used are any polymeric material, such as the plastics mentioned above.

10 Prior to the graft polymerization, the surfaces of the substrate may be activated by a variety of methods. Any standard method for activating polymer surfaces may be used here, for example the substrate may be activated prior to the graft polymerization by UV radiation, plasma treatment, corona
15 treatment, flame treatment, ozonization, electrical discharge or γ -radiation. The surfaces are usefully freed in advance in a known manner from oils, fats or other contamination, using a solvent.

The substrate may be activated using UV radiation in the wavelength range
20 from 170 to 400 nm, preferably from 170 to 250 nm. An example of a suitable radiation source is a Noblelight UV excimer apparatus from HERAEUS, Hanau, Germany. However, mercury vapor lamps are also suitable for substrate activation as long as they emit substantial proportions of radiation in the abovementioned ranges. The exposure time is generally from 0.1
25 seconds to 20 minutes, preferably from 1 second to 10 minutes.

The activation of the standard polymers with UV radiation may moreover also use a photosensitizer. For this, the photosensitizer, such as benzophenone, is applied to the substrate surface and irradiated. A mercury vapor lamp may
30 again be used here, with exposure times of from 0.1 seconds to 20 minutes, preferably from 1 second to 10 minutes.

According to the invention, the activation may also be by plasma treatment using an RF or microwave plasma (Hexagon, Technics Plasma, 85551

09926507.020702

Kirchheim, Germany) in air, nitrogen or argon atmospheres. The exposures times are generally from 2 seconds to 30 minutes, preferably from 5 seconds to 10 minutes. The energy supplied in the case of laboratory devices is from 100 to 500 W, preferably from 200 to 300 W.

5

Corona devices (SOFTAL, Hamburg, Germany) may also be used for activation. The exposure times in this case are generally from 1 to 10 minutes, preferably from 1 to 60 seconds.

- 10 Activation by electrical discharge, electron beam or γ -radiation (e.g. from a cobalt 60 source), and also ozonization, allow short exposure times, generally from 0.1 to 60 seconds.

- Substrate surfaces may also be activated by flame treatment. Suitable devices, in particular those with a barrier flame front, can readily be
15 constructed or, for example, purchased from ARCOTEC, 71297 Mönsheim, Germany. They may be operated using hydrocarbons or hydrogen as combustion gas. In all cases it is necessary to avoid damage to the substrate by overheating, and this can readily be ensured if the side of the substrate facing away from the flame treatment side is in intimate contact with a cooled
20 metal surface. Activation by flame treatment is therefore restricted to relatively thin, sheet-like substrates. The exposure times are generally from 0.1 seconds to 1 minute, preferably from 0.5 to 2 seconds. The flames are exclusively nonluminous, and the distances between the substrate surfaces and the outer side of the flame front are from 0.2 to 5 cm, preferably from 0.5
25 to 2 cm.

- The substrate surfaces activated in this way are coated by known methods, such as dipping, spraying or spreading, where appropriate in solution. Solvents which have proven useful are water and water/ethanol mixtures, but
30 other solvents may also be used as long as they are sufficiently capable of dissolving the monomers and give good wetting of the substrate surfaces. Examples of other solvents are ethanol, methanol, methyl ethyl ketone, diethyl ether, dioxane, hexane, heptane, benzene, toluene, chloroform, dichloromethane, tetrahydrofuran and acetonitrile. Solutions with monomer

"Amended page"

contents of from 1 to 10% by weight, for example about 5% by weight, have proven successful in practice and generally give, in a single pass, coherent coatings which cover the substrate surface and have thicknesses which can be more than 0.1 μm .

- 5 The graft copolymerization of the monomers applied to the activated surfaces may usefully be initiated by radiation in the short-wave segment of the visible range or in the long-wave segment of the UV range of electromagnetic radiation. For example, the radiation from a UV excimer of wavelengths from 250 to 500 nm, preferably from 290 to 320 nm, is very suitable. Mercury vapor lamps are also suitable here as long as they
- 10 have substantial proportions of radiation in the abovementioned ranges. The exposure times are generally from 10 seconds to 30 minutes, preferably from 2 to 15 minutes.

- Graft copolymerization can also be achieved by a process described in European Patent Application 0 872 512 and based on a graft polymerization of monomer molecules and
- 15 initiator molecules incorporated by swelling.

The process of the invention uses the abovementioned monomers to prepare homopolymers. There is no requirement for the use of other monomers.

- 20 Even without grafting to a substrate surface, the antimicrobial polymers prepared according to the novel process made from aliphatically unsaturated monomers which have been at least singly functionalized by means of a secondary amino group show microbicidal or antimicrobial behavior.

- 25 If the novel process is used directly on the substrate surface without grafting, conventional free-radical initiators may be used. Examples of initiators which

✓

may be used are azonitriles, alkyl peroxides, hydroperoxides, acyl peroxides, peroxoketones, peresters, peroxocarbonates, peroxodisulfate, persulfate and any of the usual photoinitiators, such as acetophenones, α -hydroxyketones, dimethylketals and benzophenone. The polymerization may also be initiated
5 thermally or, as already stated, by electromagnetic radiation, such as UV light or γ -radiation.

Use of the modified polymer substrates

The present invention also provides the use of the antimicrobial polymers
10 prepared according to the invention to produce antimicrobially active products, and the products per se which are produced in this way. The products may comprise polymer substrates modified according to the invention or consist of these. Products of this type are preferably based on polyamides, polyurethanes, polyether block amides, polyesteramides or
15 -imides, PVC, polyolefins, silicones, polysiloxanes, polymethacrylate or polyterephthalates surface-modified using polymers prepared according to the invention.

Examples of antimicrobially active products of this type are in particular machine parts for processing food and drink, components in air-conditioning
20 systems, roofing, items for bathroom and toilet use, kitchen items, components of sanitary equipment, components of cages or houses for animals, recreational products for children, components of water systems, packaging for food or drink, operator units (touch panels) of devices, and contact lenses.

25 The present invention also provides the use, to produce hygiene products or items in medical technology, of the polymer substrates whose surfaces have been modified using the antimicrobial polymers prepared according to the invention. That which has been said above concerning preferred materials
30 applies correspondingly. Examples of hygiene products of this type are toothbrushes, toilet seats, combs and packaging materials. The term hygiene items also includes objects which may come into contact with a large number of people, such as telephone handsets, stair rails, door handles, window catches, and grab straps and grab handles in public conveyances. Examples

of items in medical technology are catheters, tubing, protective or backing films and also surgical instruments.

The polymers, copolymers or graft polymers prepared by the novel process may be used anywhere where importance is placed on surfaces with release properties or surfaces which are very free from bacteria, i.e. microbicidal.

Examples of application of microbicidal polymers or graft polymers prepared according to the novel process are in particular surface coatings, protective paints and other coatings in the following sectors:

- 10 Marine: Boat hulls, docks, buoys, drilling platforms, ballast water tanks
Construction: Roofing, basements, walls, facades, greenhouses, sun protection, garden fencing, wood protection
 - Sanitary: Public conveniences, bathrooms, shower curtains, toilet items, swimming pool, sauna, jointing, sealing compounds
- 15 Requisites for daily life: Machines, kitchen, kitchen items, sponge pads, recreational products for children, packaging for food or drink, milk processing, drinking water systems, cosmetics
Machine parts: Air-conditioning systems, ion exchangers, process water, solar-powered units, heat exchangers, bioreactors, membranes
- 20 Medical technology: Contact lenses, diapers, membranes, implants
Consumer articles: Automobile seats, clothing (socks, sport clothing), hospital equipment, door handles, telephone handsets, public conveyances, animal cages, cash registers, wall-to-wall carpets, wallpapers.
- 25 The following examples are given in order to describe the present invention in greater detail, but are not intended to limit its scope as set out in the claims.

09926507.020702

Example 1:

A nylon-12 film is exposed for 2 minutes at a pressure of 1 mbar to radiation at 172 nm from a Heraeus excimer source. The film activated in this way is placed into an irradiator under inert gas and held in place. In a countercurrent of inert gas the film is then covered with 20 ml of a mixture of 3 g of methyl 2-acrylamido-2-methoxyacetate (Aldrich) and 97 g of methanol. The radiation chamber is sealed and placed at a distance of 10 cm from a Heraeus excimer unit emitting at 308 nm. Irradiation is begun and continued for 15 minutes. The film is then removed and rinsed with 30 ml of methanol, then dried in vacuo for 12 hours at 50°C. The film is then extracted in water 5 times for 6 hours at 30°C, then dried at 50°C for 12 hours.

The reverse side of the film is then treated in the same way, finally giving a polyamide film coated on both sides with grafted polymer.

15 Example 1a:

A coated piece of film from Example 1 (5 by 4 cm) is shaken in 30 ml of a test microbial suspension of Staphylococcus aureus. After a contact time of 15 minutes, 1 ml of the test suspension is removed and the number of microbes in the test mixture is determined. After expiry of this time no Staphylococcus aureus microbes are now detectable.

Example 1b:

A coated piece of film from Example 1 (5 by 4 cm) is shaken in 30 ml of a test microbial suspension of Pseudomonas aeruginosa. After a contact time of 60 minutes, 1 ml of the test suspension is removed and the number of microbes in the test mixture is determined. After expiry of this time the number of microbes has fallen from 10^7 to 10^4 .

Example 2:

30 A nylon-12 film is exposed for 2 minutes at a pressure of 1 mbar to radiation at 172 nm from a Heraeus excimer source. The film activated in this way is placed into an irradiator under inert gas and held in place. In a countercurrent of inert gas the film is then covered with 20 ml of a mixture of 3 g of methyl 2-acetamidoacrylate (Aldrich) and 97 g of methanol. The radiation chamber

09926507 020702

is sealed and placed at a distance of 10 cm from a Heraeus excimer unit emitting at 308 nm. Irradiation is begun and continued for 15 minutes. The film is then removed and rinsed with 30 ml of methanol, then dried in vacuo for 12 hours at 50°C. The film is then extracted in water 5 times for 6 hours at 30°C, then dried at 50°C for 12 hours.

The reverse side of the film is then treated in the same way, finally giving a polyamide film coated on both sides with grafted polymer.

Example 2a:

- 10 A coated piece of film from Example 2 (5 by 4 cm) is shaken in 30 ml of a test microbial suspension of Staphylococcus aureus. After a contact time of 15 minutes, 1 ml of the test suspension is removed and the number of microbes in the test mixture is determined. After expiry of this time the number of microbes has fallen from 10^7 to 10^4 .

15

Example 2b:

- A coated piece of film from Example 2 (5 by 4 cm) is shaken in 30 ml of a test microbial suspension of Pseudomonas aeruginosa. After a contact time of 60 minutes, 1 ml of the test suspension is removed and the number of microbes in the test mixture is determined. After expiry of this time the number of microbes has fallen from 10^7 to 10^4 .

20

Example 3:

- A nylon-12 film is exposed for 2 minutes at a pressure of 1 mbar to radiation at 172 nm from a Heraeus excimer source. The film activated in this way is placed into an irradiator under inert gas and held in place. In a countercurrent of inert gas the film is then covered with 20 ml of a mixture of 3 g of N-tert-butylacrylamide (Aldrich) and 97 g of methanol. The radiation chamber is sealed and placed at a distance of 10 cm from a Heraeus excimer unit emitting at 308 nm. Irradiation is begun and continued for 15 minutes. The film is then removed and rinsed with 30 ml of methanol, then dried in vacuo for 12 hours at 50°C. The film is then extracted in water 5 times for 6 hours at 30°C, then dried at 50°C for 12 hours.

25

30

The reverse side of the film is then treated in the same way, finally giving a

09926507-020702

polyamide film coated on both sides with grafted polymer.

Example 3a:

5 A coated piece of film from Example 3 (5 by 4 cm) is shaken in 30 ml of a test microbial suspension of *Staphylococcus aureus*. After a contact time of 15 minutes, 1 ml of the test suspension is removed and the number of microbes in the test mixture is determined. After expiry of this time no *Staphylococcus aureus* microbes are now detectable.

10 Example 3b:

A coated piece of film from Example 3 (5 by 4 cm) is shaken in 30 ml of a test microbial suspension of *Pseudomonas aeruginosa*. After a contact time of 60 minutes, 1 ml of the test suspension is removed and the number of microbes in the test mixture is determined. After expiry of this time the number
15 of microbes has fallen from 10^7 to 10^4 .

Example 4:

A nylon-12 film is exposed for 2 minutes at a pressure of 1 mbar to radiation at 172 nm from a Heraeus excimer source. The film activated in this way is
20 placed into an irradiator under inert gas and held in place. In a countercurrent of inert gas the film is then covered with 20 ml of a mixture of 3 g of methyl 2-acrylamido-2-methoxyacetate (Aldrich), 2 g of methyl methacrylate (Aldrich) and 95 g of methanol. The radiation chamber is sealed and placed at a distance of 10 cm from a Heraeus excimer unit emitting at 308 nm. Irradiation
25 is begun and continued for 15 minutes. The film is then removed and rinsed with 30 ml of methanol, then dried in vacuo for 12 hours at 50°C. The film is then extracted in water 5 times for 6 hours at 30°C, then dried at 50°C for 12 hours.

The reverse side of the film is then treated in the same way, finally giving a
30 polyamide film coated on both sides with grafted polymer.

Example 4a:

A coated piece of film from Example 4 (5 by 4 cm) is shaken in 30 ml of a test microbial suspension of *Staphylococcus aureus*. After a contact time of

099265507 020702

15 minutes, 1 ml of the test suspension is removed and the number of microbes in the test mixture is determined. After expiry of this time no *Staphylococcus aureus* microbes are now detectable.

5 Example 4b:

A coated piece of film from Example 4 (5 by 4 cm) is shaken in 30 ml of a test microbial suspension of *Pseudomonas aeruginosa*. After a contact time of 60 minutes, 1 ml of the test suspension is removed and the number of microbes in the test mixture is determined. After expiry of this time the number
10 of microbes has fallen from 10^7 to 10^4 .

Example 5:

A nylon-12 film is exposed for 2 minutes at a pressure of 1 mbar to radiation at 172 nm from a Heraeus excimer source. The film activated in this way is
15 placed into an irradiator under inert gas and held in place. In a countercurrent of inert gas the film is then covered with 20 ml of a mixture of 3 g of methyl 2-acetamidoacrylate (Aldrich), 2 g of methyl methacrylate (Aldrich) and 95 g of methanol. The radiation chamber is sealed and placed at a distance of 10 cm from a Heraeus excimer unit emitting at 308 nm. Irradiation is begun
20 and continued for 15 minutes. The film is then removed and rinsed with 30 ml of methanol, then dried in vacuo for 12 hours at 50°C. The film is then extracted in water 5 times for 6 hours at 30°C, then dried at 50°C for 12 hours.

The reverse side of the film is then treated in the same way, finally giving a
25 polyamide film coated on both sides with grafted polymer.

Example 5a:

A coated piece of film from Example 5 (5 by 4 cm) is shaken in 30 ml of a test microbial suspension of *Staphylococcus aureus*. After a contact time of
30 15 minutes, 1 ml of the test suspension is removed and the number of microbes in the test mixture is determined. After expiry of this time no *Staphylococcus aureus* microbes are now detectable.

Example 5b:

09926507.020702

A coated piece of film from Example 5 (5 by 4 cm) is shaken in 30 ml of a test microbial suspension of *Pseudomonas aeruginosa*. After a contact time of 60 minutes, 1 ml of the test suspension is removed and the number of microbes in the test mixture is determined. After expiry of this time the number
5 of microbes has fallen from 10^7 to 10^4 .

In addition to the microbicidal action described above with respect to cells of *Pseudomonas aeruginosa* and *Staphylococcus aureus*, all of the specimens also exhibited microbicidal action with respect to cells of *Klebsiella*
10 *pneumoniae*, *Escherichia coli*, *Rhizopus oryzae*, *Candida tropicalis* and *Tetrahymena pyriformis*.

20200207 09:26:50

What is claimed is:

1. A process for preparing antimicrobial polymers,
which comprises
5 polymerizing aliphatically unsaturated monomers which have been at least singly
functionalized by means of a secondary amino group.

2. The process as claimed in claim 1,
wherein
10 aliphatically unsaturated monomers functionalized by means of a secondary
amino group and having the general formula



15 where R^1 is a branched, unbranched or cyclic, saturated or unsaturated
hydrocarbon radical having up to 50 carbon atoms which
may have substitution by O atoms, N atoms or S atoms,
and

R^2 is a branched, unbranched or cyclic, saturated or
20 unsaturated hydrocarbon radical having up to 25 carbon
atoms, which may have substitution by O atoms, N
atoms or S atoms,

are used.

25 3. The process as claimed in claim 1 or 2,
wherein
the polymerization is carried out on a substrate.

30 4. The process as claimed in one of claims 1 to 3,
wherein
the polymerization is carried out as a graft polymerization of a substrate.

5. The process as claimed in claim 4,

"Amended page"

wherein

the substrate is activated prior to the graft polymerization by UV radiation, plasma treatment, corona treatment, flame treatment, ozonization, electrical discharge or γ -radiation.

5

6. The process as claimed in claim 4,
wherein

the substrate is activated prior to the graft polymerization by UV radiation with a photosensitizer.

10

7. The use of the antimicrobial polymers prepared as claimed in one of claims 1 to 6 for producing products with an antimicrobial coating made from the polymer.

8. The use of the antimicrobial polymers prepared as claimed in one of claims 1 to 6 for producing items in medical technology with an antimicrobial coating made from the polymer.

15

9. The use of antimicrobial polymers prepared as claimed in one of claims 1 to 6 for producing hygiene items with an antimicrobial coating made from the polymer.

20

10. The use of the antimicrobial polymers prepared as claimed in one of claims 1 to 6 in surface coatings, in protective paints or in other coatings.

09/26/2007 10:20:02

Declaration and Power of Attorney For Patent Application

Erklärung Für Patentanmeldungen Mit Vollmacht

German Language Declaration

Als nachstehend benannter Erfinder erkläre ich hiermit an Eides Statt:

dass mein Wohnsitz, meine Postanschrift, und meine Staatsangehörigkeit den im Nachstehenden nach meinem Namen aufgeführten Angaben entsprechen,

dass ich, nach bestem Wissen der ursprüngliche, erste und alleinige Erfinder (falls nachstehend nur ein Name angegeben ist) oder ein ursprünglicher, erster und Miterfinder (falls nachstehend mehrere Namen aufgeführt sind) des Gegenstandes bin, für den dieser Antrag gestellt wird und für den ein Patent beantragt wird für die Erfindung mit dem Titel:

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

PROCESS FOR PREPARING INHERENTLY

MICROBICIDAL POLYMER SURFACES

deren Beschreibung

(zutreffendes ankreuzen)

☐ hier beigefügt ist.

☐ am _____ unter der

Anmeldungsseriennummer _____

eingereicht wurde und am _____
abgeändert wurde (falls tatsächlich abgeändert).

the specification of which

(check one)

☐ is attached hereto.

☒ was filed on March, 30, 2000 as

Application Serial No. PCT/EP00/02780

and was amended on _____
(if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

Ich erkenne meine Pflicht zur Offenbarung irgendwelcher Informationen, die für die Prüfung der vorliegenden Anmeldung in Einklang mit Absatz 37, Bundesgesetzbuch, Paragraph 1.56(a) von Wichtigkeit sind, an.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, §1.56(a).

Ich beanspruche hiermit ausländische Prioritätsvorteile gemäss Abschnitt 35 der Zivilprozessordnung der Vereinigten Staaten, Paragraph 119 aller unten angegebenen Auslandsanmeldungen für ein Patent oder eine Erfindersurkunde, und habe auch alle Auslandsanmeldungen für ein Patent oder eine Erfindersurkunde nachstehend gekennzeichnet, die ein Anmeldedatum haben, das vor dem Anmeldedatum der Anmeldung liegt, für die Priorität beansprucht wird.

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

German Language Declaration

Ich beanspruche hiermit ausländische Prioritätsvorteile gemäß Title 35, US-Code, § 119(a)-(d), bzw. § 365(b) aller unten aufgeführten Auslandsanmeldungen für Patente oder Erfinderurkunden, oder § 365(a) aller PCT internationalen Anmeldungen, welche wenigstens ein Land ausser den Vereinigten Staaten von Amerika benennen, und habe nachstehend durch ankreuzen sämtliche Auslandsanmeldungen für Patente bzw. Erfinderurkunden oder PCT internationale Anmeldungen angegeben, deren Anmeldetag dem der Anmeldung, für welche Priorität beansprucht wird, vorangeht.

I hereby claim foreign priority under Title 35, United States Code, § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below, and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

Prior foreign application(s)
(Frühere ausländische Anmeldungen)

Priority claimed

Priorität
beansprucht

199 21 900.1 GERMANY
(Number) (Country)
(Nummer) (Land)

May 12, 1999
(Day/Month/Year Filed)
(Tag/Monat/Jahr der Anmeldung)

☒ Yes ☐ No
Ja Nein

(Number) (Country)
(Nummer) (Land)

(Day/Month/Year Filed)
(Tag/Monat/Jahr der Anmeldung)

☐ Yes ☐ No
Ja Nein

Ich Beanspruche hiermit Prioritätsvorteile unter Title 35, US-Code, § 119(e) aller US-Hilfsanmeldungen wie unten aufgezählt.

I hereby claim the benefit under Title 35, United States Code, § 119(e) of any United States provisional application(s) listed below.

(Application No.)
(Aktenzeichen)

(Filing Date)
(Anmeldetag)

(Application No.)
(Aktenzeichen)

(Filing Date)
(Anmeldetag)

Ich beanspruche hiermit die mir unter Title 35, US-Code, § 120 zustehenden Vorteile aller unten aufgeführten US-Patentanmeldungen bzw. § 365(c) aller PCT internationalen Anmeldungen, welche die Vereinigten Staaten von Amerika benennen, und erkenne, insofern der Gegenstand eines jeden früheren Anspruchs dieser Patentanmeldung nicht in einer US-Patentanmeldung, bzw. PCT internationalen Anmeldung in in einer gemäß dem ersten Absatz von Title 35, US-Code, § 112 vorgeschriebenen Art und Weise offenbart wurde, meine Pflicht zur Offenbarung jeglicher Informationen an, die zur Prüfung der Patentfähigkeit in Einklang mit Title 37, Code of Federal Regulations, § 1.56 von Belang sind und die im Zeitraum zwischen dem Anmeldetag der früheren Patentanmeldung und dem nationalen oder im Rahmen des Vertrags über die Zusammenarbeit auf dem Gebiet des Patentwesens (PCT) gültigen internationalen Anmeldetags bekannt geworden sind.

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s), or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application.

PCT/EP00/02780

March, 30, 2000

(Application No.)
(Aktenzeichen)

(Filing Date)
(Anmeldetag)

pending

(Status) (patented, pending, abandoned)
(Status) (patentiert, schwebend, aufgegeben)

(Application No.)
(Aktenzeichen)

(Filing Date)
(Anmeldetag)

(Status) (patented, pending, abandoned)
(Status) (patentiert, schwebend, aufgegeben)

Ich erkläre hiermit, daß alle in der vorliegenden Erklärung von mir gemachten Angaben nach bestem Wissen und Gewissen der Wahrheit entsprechen, und ferner daß ich diese eidesstattliche Erklärung in Kenntnis dessen ablege, daß wissentlich und vorsätzlich falsche Angaben oder dergleichen gemäß § 1001, Title 18 des US-Code strafbar sind und mit Geldstrafe und/oder Gefängnis bestraft werden können und daß derartige wissentlich und vorsätzlich falsche Angaben die Rechtswirksamkeit der vorliegenden Patentanmeldung oder eines aufgrund deren erteilten Patentes gefährden können.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

German Language Declaration

VERTRETUNGSVOLLMACHT: Als benannter Erfinder beauftrage ich hiermit den nachstehend benannten Patentanwalt (oder die nachstehend benannten Patentanwälte) und/oder Patent-Agenten mit der Verfolgung der vorliegenden Patentanmeldung sowie mit der Abwicklung aller damit verbundenen Geschäfte vor dem Patent- und Warenzeichenamt: (Name und Registrationsnummer anführen)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith. (list name and registration number)

Norman F. Oblon, Registration Number 24,618; Marvin J. Spivak, Registration Number 24,913; C. Irvin McClelland, Registration Number 21,124; Gregory J. Maier, Registration Number 25,599; Arthur I. Neustadt, Registration Number 24,854; Richard D. Kelly, Registration Number 27,757; James D. Hamilton, Registration Number 28,421; Eckhard H. Kuesters, Registration Number 28,870; Robert T. Pous, Registration Number 29,099; Charles L. Gholz, Registration Number 26,395; Vincent J. Sunderdick, Registration Number 29,004; William E. Beaumont, Registration Number 30,996; Steven B. Kelber, Registration Number 30,073; Robert F. Gnuse, Registration Number 27,295; Jean-Paul Lavalleye, Registration Number 31,451; Stephen G. Baxter, Registration Number 32,884; Martin M. Zoltick, Registration Number 35,745; Robert W. Hahl, Registration Number 33,893; Richard L. Treanor, Registration Number 36,379; Steven P. Weihrouch, Registration Number 32,829; John T. Goolkasian, Registration Number 26,142; Marc R. Labgold, Registration Number 34,651; William J. Healey, Registration Number 36,160; Richard L. Chinn, Registration Number 34,305; Steven E. Lipman, Registration Number 30,011; Carl E. Schlier, Registration Number 34,426; James J. Kulbaski, Registration Number 34,648; Catherine B. Richardson, Registration Number 39,007; Richard A. Neifeld, Registration Number 35,299; and J. Derek Mason, Registration Number 35,270; with full powers of substitution and revocation.

Telefongespräche bitte richten an:
(Name und Telefonnummer)



Direct Telephone Calls to: (name and telephone number)

(703) 413-3000

Postanschrift:

Send Correspondence to:

OBLON, SPIVAK, MCCLELLAND, MAIER & NEUSTADT, P.C.
FOURTH FLOOR
1755 JEFFERSON DAVIS HIGHWAY
ARLINGTON, VIRGINIA 22202 U.S.A.

Voller Name des einzigen oder ursprünglichen Erfinders: <u>1-00</u>		Full name of sole or first inventor: <u>Peter OITERSBACH</u>	09. NOV. 2001
Unterschrift des Erfinders	Datum	Inventor's signature: 	Date
Wohnsitz		Residence: <u>Windeck, GERMANY DEX</u>	
Staatsangehörigkeit		Citizenship: <u>GERMANY</u>	
Postanschrift		Post Office Address: <u>Zum Beuel 14, 51570 Windeck, GERMANY</u>	
Voller Name des zweiten Miterfinders (falls zutreffend): <u>2-00</u>		Full name of second joint inventor, if any: <u>Beate KOSSMANN</u>	09. NOV. 2001
Unterschrift des Erfinders	Datum	Second inventor's signature: 	Date
Wohnsitz		Residence: <u>Hagen, GERMANY DEX</u>	
Staatsangehörigkeit		Citizenship: <u>GERMANY</u>	
Postanschrift		Post Office Address: <u>Ribbertstraße 13, 58091 Hagen, GERMANY</u>	

(Bitte entsprechende Informationen und Unterschriften im Falle von dritten und weiteren Miterfindern angeben.)

(Supply similar information and signature for third and subsequent joint inventors.)